

Products description

Metallic polyurethane material for heat transfer applications.

Thickness : 60 microns (USA : 2,4 mil).

Carrier : self-adhesive and transparent polyester.

Suitable for

HOTMARK Metallic : Cotton, polyester, acrylic and similar fibres.

ALLMARK Metallic : Nylon.

Application advises

- 1) Cut the material in reverse with a flex blade.
- 2) Weed the excess material.
- 3) Heat press the image on the garment with its polyester carrier protected by a silicone paper at 140°C (USA : 280°F) – 15-20 seconds – medium pressure.
- 4) Peel the carrier off when cold.

Maintenance

Always respect the instructions mentioned on garments.

After heat pressing, wait 24 hours before the first wash.

Washing : hand and cold washing - without bleach or any aggressive washing products.

Dried cleaning : no

Ironing : backside

Storage of the roll : vertically, one year in a dry room, 15-30°C (USA : 60-85°F), protected from sunlight.

Caution

Be careful with the metallic quality : Never heat press twice this product.

Those recommendations are based on our own experiences.

We always recommend making trials before starting standard production.

July 2009

CHEMICA

8 rue Auguste Poncetton
42000 Saint-Etienne – France
Tel : +33.(0)4.77.49.20.90
Fax : +33.(0)4.77.25.79.82
info@chemica.fr - www.chemica.fr

CHEMICA US

3495 Piedmont Road – Bldg 11, Suite 710
Atlanta, GA 30305 – USA
Tel : +1 404.495.5991 – cell +1.404.754.0548
Fax : +1.404.233.8625
rosa.lopes@chemica.fr – www.chemica.fr