

Product description

Viscose flock material (velvet touch) for heat transfer applications.

Fibres thickness : 0,75 mm (USA : 25-30 mil).

Carrier : self-adhesive and transparent polyester.

Norm : Oekotex label.

Suitable for

Cotton, polyester, acrylic and similar fibres.

Application advises

- 1) Cut the material in reverse with a flock blade.
- 2) Weed the excess material.
- 3) Heat press the image on the garment with its polyester carrier protected by a silicone paper at 160°C (USA : 320°F) – 15-20 seconds – medium pressure.
- 4) Peel the carrier off when cold.

Maintenance

Always respect the instructions mentioned on garments
After heat pressing, wait 24 hours before the first wash.

Washing : 90°C (USA : 190°F) max. inside out - without bleach or any aggressive washing products.
After first washing, the fibres are getting higher and smoother.

Dried cleaning : yes

Ironing : backside

Storage of the roll : vertically, one year in a dry room, 15-30°C (USA : 60-85°F), protected from sunlight.

Caution

Those recommendations are based on our own experiences.
We always recommend making trials before starting standard production.

May 2009

CHEMICA

8 rue Auguste Poncetton
42000 Saint-Etienne – France
Tel : +33.(0)4.77.49.20.90
Fax : +33.(0)4.77.25.79.82
info@chemica.fr - www.chemica.fr

CHEMICA US

3495 Piedmont Road – Bldg 11, Suite 710
Atlanta, GA 30305 – USA
Tel : +1 404.495.5991 – cell +1.404.754.0548
Fax : +1.404.233.8625
rosa.lopes@chemica.fr – www.chemica.fr